

Amendment to Claims: This Listing of Claims will replace all prior versions and listings of claims in the Application.

Please cancel claims 1-13, and add claims 25 – 58.

5

#### LISTING OF CLAIMS

Claims 1-13 (Canceled)

Claims 14-24 are withdrawn from consideration due to a restriction.

- 10 25. (New) A moisture curable adhesive, comprising:
- a) a polymer or copolymer having reactive silicon end groups;
  - 15 b) from about from about 5 to about 90 weight percent of a filler, which includes fumed silica having a surface area of less than 200 m<sup>2</sup>/gram ; and
  - c) from about 0.01 to about 10 percent by weight of a dehydrating agent.
- 20 26. (New) The moisture curable adhesive in claim 25, wherein the adhesive has a viscosity of from about 1,000 to about 500,000 centipoise.
- 25 27. (New) The moisture curable adhesive in claim 25, wherein the adhesive has a viscosity of from about 1,000 to about 200,000 centipoise.
28. (New) The moisture curable adhesive in claim 25, wherein the amount of filler is from about 20 to about 85 percent by weight.
- 30 29. (New) The moisture curable adhesive in claim 25, wherein the amount of filler is from about 35 to about 85 percent by weight.

30. (New) The moisture curable adhesive in claim 25, wherein the amount of filler is from about 43 to about 85 percent by weight.
- 5 31. (New) The moisture curable adhesive in claim 25, wherein the amount of filler is from about 60 to about 85 percent by weight.
32. (New) The moisture curable adhesive in claim 25, wherein the filler includes a filler having a surface area of less than  $150 \text{ m}^2/\text{gram}$
- 10 33. (New) The moisture curable adhesive in claim 25, wherein the filler includes a filler having a surface area of less than  $75 \text{ m}^2/\text{gram}$
34. (New) The moisture curable adhesive in claim 25, wherein the filler includes a filler having a surface area of less than  $50 \text{ m}^2/\text{gram}$
- 15 35. (New) The moisture curable adhesive in claim 25, wherein the filler with the surface area less than  $250 \text{ m}^2/\text{grams}$  is fumed amorphous silica.
- 20 36. (New) The moisture curable adhesive in claim 25, which includes calcium carbonate as a filler.
- 25 37. (New) The moisture curable adhesive in claim 25 which has filler selected from: zinc oxide; reinforcing, semi-reinforcing, and non-reinforcing carbon blacks; white carbon; expanded graphite powders; powdery graphite; crystalline silica; molten silica; silicates; chalk; calcium carbonate including limestone; talc; mica; alumina; aluminum hydroxide; zirconia; titanium dioxide; wollastonite; feldspar; aluminum silicate; solid and hollow ceramic microspheres hollow spheres, ceramic and plastic; metal powders and microbeads; wood flour; dolomite; organic or inorganic pigments, or combinations thereof.
- 30

38. (New) The moisture curable adhesive in claim 25, wherein the adhesive further comprises at least one of a catalyst; anti-oxidants, lubricants, extenders, biocides, adhesion promoters, UV absorbers and stablizers.

5 39. (New) The moisture curable adhesive in claim 25, wherein the catalyst is present in an amount from about 0.01 to about 2.5 percent by weight.

40. (New) The moisture curable adhesive in claim 25, wherein the dehydrating agents is selected from vinyl trimethoxysilane, any vinyl alkoxysilane, or  
10 inorganic or organic zeolites.

41. (New) The moisture curable adhesive in claim 25, wherein the adhesion promoter is present in an amount of about 0.01 to about 5 % by weight.

15 42. (New) The moisture curable adhesive in claim 25, wherein the anti-oxidant is present in an amount from about 0.01 to about 4 % by weight.

43. (New) The moisture curable adhesive in claim 25, wherein the polymer or copolymer having reactive silicon end groups is present in an amount of  
20 about 10 to about 50 percent by weight

44. (New) A moisture curable adhesive, comprising:

a) a polymer or copolymer having reactive silicon end groups;

25 b) from about .01 to about 50 percent by weight of a clear filler that will not substantially interfere with the production of clear adhesive selected from: i) fumed silica with a surface area of less than 150 m<sup>2</sup>/gram, or a clear filler having a surface area from 75 to less than  
30 250 m<sup>2</sup>/gram where the viscosity of the adhesive is in the range of 1,000 to about 200,000 centipoise; and

c) from about 0.01 to about 10 percent by weight of a dehydrating agent

5 45. (New) The moisture curable adhesive in claim 44, wherein the adhesive has a viscosity from about 1,000 to about 200,000 centipoise.

46. (New) The moisture curable adhesive in claim 44, wherein the glass transition temperature of the adhesive is less than about -20 °C.

10

47. (New) The moisture curable adhesive in claim 44, wherein the service temperature range of the adhesive is from about -60°C to about 160 °C.

15

48. (New) The moisture curable adhesive in claim 44, wherein the clear filler is fumed amorphous silica.

49. (New) The moisture curable adhesive in claim 44, wherein the polymer or copolymer having reactive silicon end groups is present in an amount of about 50 to about 90 percent by weight.

20

50. (New) The moisture curable adhesive in claim 44, wherein the polymer or copolymer having reactive silicon end groups is present in an amount of about 65 to about 80 percent by weight and the polymer or copolymer is selected from polyalkyl oxide; any polyalkane, alkene, or alkyne; polymers of substituted alkyl monomers of styrene; acrylics or any polymer or  
25 copolymer that can be prepared with the silyl, reactive silicon, end groups or combinations thereof, and where the polymer or copolymer has reactive silicon end groups selected from triethoxysilane, methyldiethoxysilane, trisilanol, any alkoxysilane, substituted silane, multi-silanol, or  
30 combinations thereof.

51. (New) The moisture curable adhesive in claim 44, wherein the amount of filler is from about 5 to about 20 percent by weight.
52. (New) The moisture curable adhesive in claim 44, wherein the filler  
5 includes a filler having a surface area of less than 75 m<sup>2</sup>/gram
53. (New) The moisture curable adhesive in claim 44, wherein the filler includes a blend of fillers one having a surface area of 50 m<sup>2</sup>/gram and another one having a surface area of 110 m<sup>2</sup>/gram.
- 10 54. (New) The moisture curable adhesive in claim 44, wherein the adhesive further comprises at least one of a catalyst; anti-oxidants, lubricants, extenders, biocides, adhesion promoters, UV absorbers and stablizers.
- 15 55. (New) The moisture curable adhesive in claim 44, wherein the catalyst is present in an amount from about 0.01 to about 2.5 percent by weight.
56. (New) The moisture curable adhesive in claim 44, wherein the dehydrating agents is selected from vinyl trimethoxysilane, any vinyl alkoxysilane, or  
20 inorganic or organic zeolites.
57. (New) The moisture curable adhesive in claim 44, wherein the adhesion promoter is present in an amount of about 0.01 to about 5 % by weight.
- 25 58. (New) The moisture curable adhesive in claim 25, wherein the anti-oxidant is present in an amount from about 0.01 to about 4 % by weight.